## REMARKS

By this amendment, Claims 1-8 have been canceled and Claims 9-64 have been added. Examination and allowance of Claims 9-64 are respectfully requested.

Respectfully submitted,

CHRISTENSEN O'CONNOR JOHNSON KINDNESSPILE

Ceans 6 Ventoni

George E. Řenzoni, Ph.D. Registration No. 37,919

Direct Dial No. 206.695.1755

I hereby certify that this correspondence is being deposited with the U.S. Postal Service in a sealed envelope as first class mail with postage thereon fully prepaid and addressed to the Commissioner for Patents, U.S. Patent and Trademark Office, P.O. Box 2327, Arlington, MA 22207, on the below date.

Date: February 28, 2002

GER:md/ws

## **VERSION WITH MARKINGS TO SHOW CHANGES MADE FEBRUARY 28, 2002**

## In the Specification:

The paragraph on page 40, beginning at line 11 has been amended as follows:

The electro-optic coefficient (picometers/volt, pm/V, at 1.3 microns), r<sub>33</sub>, as a function of chromophore loading (weight percent) was determined as described above for a corresponding chromophore having a tricyanofuran acceptor [this chromophore] in amorphous polycarbonate. The results are illustrated in FIGURE 18. Referring to FIGURE 18, the greatest electro-optic coefficient (66 pm/V) was measured at 30 weight percent chromophore and electro-optic coefficients of 64 pm/V were achieved for loadings of 28 and 35 weight percent chromophore. Electro-optic coefficients of 47 and 57 pm/V were achieved at 20 and 30 weight percent chromophore, respectively.

Claims 1 - 8 have been cancelled and Claims 9 - 64 have been added.